

LyondellBasell Petrothene® LP500210 High Density Polyethylene (Sheet & Profile Grade)

Category: Polymer, Thermoplastic, Polyethylene (PE), HDPE, High Density Polyethylene (HDPE), Sheet/Thermoforming Grade

Material Notes:

ApplicationsThe PETROTHENE LP 5002 series of polyethylene resins exhibits excellent environmental stress crack resistance. Regulatory StatusThe LP 5002 base resin meets the requirements of Food and Drug Administration regulation, 21 CFR 177.1520. This regulation allows the use of this olefin polymer in "articles or components of articles intended for use in contact with food." Specific limitations or conditions of use may apply. Contact your Equistar sales representative for more information. Processing TechniquesSpecific recommendations for processing LP 5002 can only be made when the processing conditions, equipment and end use are known. For further suggestions, please contact your Equistar sales representative. This product is from the former Equistar product line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_LyondellBasell-Petrothene-LP500210-High-Density-Polyethylene-Sheet-Profile-Grade.php

Physical Properties	Metric	English	Comments
Density	0.946 g/cc	0.0342 lb/in³	ASTM D1505
Environmental Stress Crack Resistance	>= 1000 hour	>= 1000 hour	F ₅₀ ; ASTM D1693
ESCR, Bottle	>= 1000 hour	>= 1000 hour	F ₅₀ ; ASTM D2561
Melt Flow	0.20 g/10 min	0.20 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	65	65	ASTM D2240
Tensile Strength, Yield	23.4 MPa	3400 psi	ASTM D638
Elongation at Break	>= 800 %	>= 800 %	ASTM D638
Flexural Modulus	0.965 GPa	140 ksi	ASTM D790
Tensile Impact	131 J/cm	245 ft-lb/in	ASTM D1822

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	66.0 °C	151 °F	ASTM D648
Vicat Softening Point	122 °C	252 °F	ASTM D1525
Brittleness Temperature	<= -76.0 °C	<= -105 °F	F ₅₀ ; ASTM D746

Descriptive Properties	Value	Comments
Antistat	High	



Descriptive Properties

Value

Comments

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China