

## LyondellBasell Petrothene® LR734001 High Density Polyethylene (Blow Molding Grade)

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), Blow Molding Grade

### Material Notes:

**Applications**The PETROTHENE LR 7340 series of polyethylene resins exhibits good stiffness and ESCR. Typical applications include bottles for household chemicals.  
**Regulatory Status**The base resin LR 7340 meets the requirements of Food and Drug Administration regulation, 21 CFR 177.1520. This regulation allows the use of this olefin polymer in "articles or components of articles intended for use in contact with food." Specific limitations or conditions of use may apply. Contact your Equistar sales representative for more information.  
**Processing Techniques**Specific recommendations for processing LR 7340 can only be made when the processing conditions, equipment and end use are known. For further suggestions, please contact your Equistar sales representative.This product is from the former Equistar product line.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_LyondellBasell-Petrothene-LR734001-High-Density-Polyethylene-Blow-Molding-Grade.php](http://www.lookpolymers.com/polymer_LyondellBasell-Petrothene-LR734001-High-Density-Polyethylene-Blow-Molding-Grade.php)

Physical Properties	Metric	English	Comments
Density	0.953 g/cc	0.0344 lb/in <sup>3</sup>	ASTM D1505
Environmental Stress Crack Resistance	25 hour	25 hour	F <sub>50</sub> ; ASTM D1693
ESCR, Bottle	>= 500 hour	>= 500 hour	F <sub>50</sub> ; ASTM D2561
Melt Flow	0.38 g/10 min	0.38 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	67	67	ASTM D2240
Tensile Strength, Yield	27.6 MPa	4000 psi	ASTM D638
Elongation at Break	>= 500 %	>= 500 %	ASTM D638
Flexural Modulus	1.21 GPa	176 ksi	ASTM D790
Tensile Impact	69.9 J/cm	131 ft-lb/in	ASTM D1822

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	75.0 °C	167 °F	ASTM D648
Vicat Softening Point	127 °C	261 °F	ASTM D1525
Brittleness Temperature	<= -76.0 °C	<= -105 °F	F <sub>50</sub> ; ASTM D746

**Contact Songhan Plastic Technology Co.,Ltd.**

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China