

## LyondellBasell Petrothene® NA940085 Low Density Polyethylene (Film Grade)

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , LDPE , Low Density Polyethylene (LDPE), Film Grade

### Material Notes:

**Applications**PETROTHENE NA 940 is a series of resins designed for heavy duty film applications. Superior puncture resistance combined with excellent impact properties make NA 940 an ideal choice for bags used to package fertilizer, peat moss, decorative stone and agricultural and construction materials. **Regulatory Status**NA 940 meets the requirements of the Food and Drug Administration regulation, 21 CFR 177.1520. This regulation allows the use of this olefin polymer in "articles or components of articles intended for use in contact with food." Specific limitations or conditions of use may apply. Contact your Equistar sales representative for more information.

**Processing Techniques**NA 940 has been designed for excellent processability, bubble stability and good heat sealing over a wide range of extrusion conditions. Optimum properties are found at melt temperatures of 330°-430°F and blow-up ratios between 1.8:1 and 2.5:1.

Drawdown to 1.5 mil is possible at commercial rates when properThis product is from the former Equistar product line.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_LyondellBasell-Petrothene-NA940085-Low-Density-Polyethylene-Film-Grade.php](http://www.lookpolymers.com/polymer_LyondellBasell-Petrothene-NA940085-Low-Density-Polyethylene-Film-Grade.php)

Physical Properties	Metric	English	Comments
Density	0.918 g/cc	0.0332 lb/in <sup>3</sup>	ASTM D1505
Environmental Stress Crack Resistance	>= 168 hour	>= 168 hour	Cond. A 100% Igepal, 0 failures in 7 days; ASTM D1693
Thickness	50.8 microns	2.00 mil	2:1 BUR; 25 mil die gap
Melt Flow	0.25 g/10 min	0.25 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	50	50	Molded; ASTM D2240
Tensile Strength, Yield	14.5 MPa	2100 psi	Molded; ASTM D638
Film Elongation at Break, MD	300 %	300 %	ASTM D882
Film Elongation at Break, TD	500 %	500 %	ASTM D882
Elongation at Break	>= 600 %	>= 600 %	Molded; ASTM D638
Flexural Modulus	0.234 GPa	34.0 ksi	Molded; ASTM D790
Elmendorf Tear Strength MD	220 g	220 g	ASTM D1922
Elmendorf Tear Strength TD	200 g	200 g	ASTM D1922
Dart Drop Test	220 g	0.485 lb	F <sub>50</sub> ; ASTM D1709
Film Tensile Strength at Break, MD	20.7 MPa	3000 psi	ASTM D882

Film Tensile Strength at Break, TD Mechanical Properties	19.3 MPa Metric	2800 psi English	ASTM D882 Comments
1% Secant Modulus, MD	165 MPa	24000 psi	ASTM D882
1% Secant Modulus, TD	186 MPa	27000 psi	ASTM D882

Thermal Properties	Metric	English	Comments
Vicat Softening Point	90.0 Â°C	194 Â°F	ASTM D1525
Brittleness Temperature	<= -76.0 Â°C	<= -105 Â°F	Molded; F<sub>50</sub>; ASTM D746

Processing Properties	Metric	English	Comments
Melt Temperature	221 Â°C	430 Â°F	

Descriptive Properties	Value	Comments
Antiblock	High	
Slip	None	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China