

LyondellBasell Plexar® PX5400 Extrudable Tie-Layer Resin, Anhydride Modified LLDPE

Category : Polymer , Thermoplastic , Polyethylene (PE) , Anhydride-Modified Polyethylene , LLDPE

Material Notes:

Plexar® tie-layers are chemically modified resins used to bond unlike materials, primarily in packaging and industrial applications. Common adherents include polyethylene resins and copolymers, such as EVA or EMA, polypropylene, polyamide (nylon), ethylene vinyl alcohol copolymers (EVOH), ionomer and other sealants, polyethylene terephthalate (PET) resins and copolymers, styrenic polymers, metal, paper and many others. Product grades tailored for blown and cast films, sheet and thermoforming, blow molding, extrusion coating and lamination, tubing, pipe, spray coating and other specialty applications are available in pellet form. Contact your Plexar sales and/or Equistar technical service representative for more information and specific recommendations for your application(s). Applications: PX5400 is designed to give outstanding adhesion and optimum process-ability to polyethylene, styrenic polymers, barrier resins such as EVOH and nylon in cast, sheet, blown film and thermoforming applications. Contact your Plexar sales and/or Equistar technical service representative for additional information. Regulatory Status: PX5400 meets the requirements for the Food and Drug Administration regulation 21CFR 175.105 for adhesives. This regulation describes adhesives which may be safely used as components of articles intended for use in packaging, transporting or holding food in accordance with conditions outlined in that regulation. For an adhesive formulation to be used in compliance with Section 175.105, it must be used under conditions that prevent the material from becoming a component of food in more than insignificant, de minimis, amounts. For more information, please contact your Equistar product safety representative. Processing Techniques: A process melt temperature above 410°F (210°C) is recommended to ensure adhesion between adherents. More specific suggestions can be made only when equipment, process parameters and conditions of use are known. Contact your Equistar Plexar technical service representative for more information. This product is from the former Equistar product line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_LyondellBasell-Plexar-PX5400-Extrudable-Tie-Layer-Resin-Anhydride-Modified-LLDPE.php

Physical Properties	Metric	English	Comments
Density	0.933 g/cc	0.0337 lb/in ³	ASTM D1505
Melt Flow	3.0 g/10 min	3.0 g/10 min	ASTM D1238

Thermal Properties	Metric	English	Comments
Vicat Softening Point	88.0 °C	190 °F	ASTM D1525

Processing Properties	Metric	English	Comments
Melt Temperature	>= 210 °C	>= 410 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China