

## LyondellBasell Pro-fax 6331W Polypropylene Homopolymer, Antistat

Category : Polymer , Thermoplastic , Polypropylene (PP)

### Material Notes:

**Key Features:** antistatic polypropylene homopolymer resin, FDA acceptable, resists dust pickup, low odor transfer  
**Applications:** containers, closures, hospital and institutional ware, toys  
**Meets FDA requirements in 21 CFR 177.1520 for all food contact, including cooking applications.**  
**Description:** Pro-fax 6331W easy molding polypropylene homopolymer resin features antistatic properties. This resin is available in pellet form. It meets FDA requirements in the Code of Federal Regulations in 21 CFR 177.1520 for all food contact, including cooking applications. This resin has a UL yellow card RTI, which applies to all colors. All ingredients meet the chemical registration requirements of TSCA and DSL. Information provided by Montell Polyolefins. LyondellBasell is the successor company to Montell.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_LyondellBasell-Pro-fax-6331W-Polypropylene-Homopolymer-Antistat.php](http://www.lookpolymers.com/polymer_LyondellBasell-Pro-fax-6331W-Polypropylene-Homopolymer-Antistat.php)

Physical Properties	Metric	English	Comments
Density	0.900 g/cc	0.0325 lb/in <sup>3</sup>	ASTM D792B
Melt Flow	12 g/10 min @Load 2.16 kg, Temperature 230 °C	12 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	89	89	ASTM D785A
Tensile Strength, Yield	34.0 MPa	4930 psi	ASTM D638
Elongation at Yield	10 %	10 %	ASTM D638
Flexural Modulus	1.50 GPa	218 ksi	1% secant at 0.05 in/min; ASTM D790A
Izod Impact, Notched	0.340 J/cm	0.637 ft-lb/in	ASTM D256A

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	92.0 °C	198 °F	ASTM D648
UL RTI, Mechanical with Impact	65.0 °C	149 °F	Minimum thickness 0.038 inches.
Flammability, UL94	HB	HB	Minimum thickness 0.038 inches.

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China