

LyondellBasell Pro-fax 6524 Polypropylene Homopolymer, Heat- and Extraction-Resistant

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

Key Features: heat and extraction-resistant polypropylene homopolymer resin, FDA acceptable, high resistance to solvents
Applications: appliances, automotive under-the-hood applications
Meets FDA requirements in 21 CFR 177.1520 for all food contact, including cooking applications.
Description: Pro-fax 6524 polypropylene homopolymer resin is highly resistant to aging at elevated temperatures in both wet and dry environments. This resin meets FDA requirements in the Code of Federal Regulations in 21 CFR 177.1520 for all food contact, including cooking applications. It has a UL yellow card RTI, which applies to all colors. All ingredients meet the chemical registration requirements of TSCA and DSL. Information provided by Montell Polyolefins. LyondellBasell is the successor company to Montell.

Order this product through the following link:

http://www.lookpolymers.com/polymer_LyondellBasell-Pro-fax-6524-Polypropylene-Homopolymer-Heat-and-Extraction-Resistant.php

Physical Properties	Metric	English	Comments
Density	0.900 g/cc	0.0325 lb/in ³	ASTM D792B
Melt Flow	4.0 g/10 min	4.0 g/10 min	ASTM D1238
	@Load 2.16 kg, Temperature 230 Â°C	@Load 4.76 lb, Temperature 446 Â°F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	85	85	ASTM D785A
Tensile Strength, Yield	34.0 MPa	4930 psi	ASTM D638
Elongation at Yield	12 %	12 %	ASTM D638
Flexural Modulus	1.40 GPa	203 ksi	1% secant at 0.05 in/min; ASTM D790A
Izod Impact, Notched	0.390 J/cm	0.731 ft-lb/in	ASTM D256A

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	90.0 Â°C	194 Â°F	ASTM D648
UL RTI, Mechanical with Impact	115 Â°C	239 Â°F	Minimum thickness 0.040 inches.
Flammability, UL94	HB	HB	Minimum thickness 0.040 inches.

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China