## LyondellBasell Pro-fax 8623 Polypropylene Impact Copolymer

Category : Polymer , Thermoplastic , Polypropylene (PP)

## Material Notes:

Key Features: super-high impact polypropylene copolymer resin, good stiffness, FDA acceptableApplications: automotive parts, luggage, totes, bins, carrying cases, appliancesMeets FDA requirements in 21 CFR 177.1520 for all food contact, excluding cooking applications.Description: Pro-fax 8623 super high impact polypropylene copolymer resin is designed for general extrusion or injection molding equipment. It has a UL yellow card RTI, which applies to all colors. This resin meets FDA requirements in the Code of Federal Regulations in 21 CFR 177.520 for all food contact, including cooking applications. All ingredients meet the chemical registration requirements of TSCA and DSL.Information provided by Montell Polyolefins.LyondellBasell is the successor company to Montell.

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_LyondellBasell-Pro-fax-8623-Polypropylene-Impact-Copolymer.php

Physical Properties	Metric	English	Comments
Density	0.900 g/cc	0.0325 lb/in³	ASTM D792B
Melt Flow	2.0 g/10 min	2.0 g/10 min	ASTM D1238
	@Load 2.16 kg, Temperature 230 °C	@Load 4.76 lb, Temperature 446 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	22.0 MPa	3190 psi	ASTM D638
Elongation at Yield	8.0 %	8.0 %	ASTM D638
Flexural Modulus	1.00 GPa	145 ksi	1% secant at 0.05 in/min; ASTM D790A
Izod Impact, Notched	NB	NB	ASTM D256A
Impact Test	>= 61.0 J	>= 45.0 ft-lb	Montell drop weight impact strength
	@Temperature -29.0 °C	@Temperature -20.2 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	82.0 °C	180 °F	ASTM D648
UL RTI, Mechanical with Impact	105 °C	221 °F	Minimum thickness 0.038 inches.
Flammability, UL94	НВ	НВ	Minimum thickness 0.038 inches.

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com



Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China