

LyondellBasell Purell® PE3220D Low Density Polyethylene, Injection Molding, Blow Fill & Seal, Extrusion Blow Molding

Category : Polymer , Thermoplastic , Polyethylene (PE) , LDPE , Low Density Polyethylene (LDPE), Blow Molding Grade

Material Notes:

Purell PE 3220 D is a low density polyethylene with high rigidity and good chemical resistance. It is delivered in pellet form. Target markets are packaging of pharmaceuticals in the small blow molding market. Regulatory Status: Purell PE 3220 D meets the requirements of the Food and Drug Administration, Code of Federal Regulations, 21CFR Section 177.1520. This regulation allows the use of this olefin polymer in "articles or components of articles intended for use in contact with food." Contact your Equistar sales representative for more information regarding the suitability of specific products for specific applications. Specific recommendations for processing Purell PE 3220 D can only be made when the processing conditions, equipment and end use are known. For further suggestions, please contact your Equistar sales representative. This product is from the former Equistar product line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_LyondellBasell-Purell-PE3220D-Low-Density-Polyethylene-Injection-Molding-Blow-Fill-Seal-Extrusion-Blow-Molding.php

Physical Properties	Metric	English	Comments
Density	0.930 g/cc	0.0336 lb/in ³	ASTM D1505
Melt Flow	0.40 g/10 min	0.40 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	13.8 MPa	2000 psi	ASTM D638
Tensile Strength, Yield	16.5 MPa	2400 psi	ASTM D638
Elongation at Break	660 %	660 %	ASTM D638
Tensile Modulus	0.483 GPa	70.0 ksi	1% Secant; ASTM D638
Flexural Modulus	0.494 GPa	71.6 ksi	1% Secant; ASTM D790

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	48.0 °C	118 °F	ASTM D648
Vicat Softening Point	107 °C	225 °F	ASTM D1525

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China