

M. Holland Company CP330 Polypropylene Impact Copolymer

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

Antistatic Impact copolymer Medium flow High impact resistance Nucleated Applications: Crates Pails Information provided by M. Holland

Order this product through the following link:

http://www.lookpolymers.com/polymer_M-Holland-Company-CP330-Polypropylene-Impact-Copolymer.php

Physical Properties	Metric	English	Comments
Density	0.905 g/cc	0.0327 lb/in ³	ASTM D1505
Melt Flow	7.0 g/10 min @Load 2.16 kg, Temperature 230 °C	7.0 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	18.6 MPa	2700 psi	ASTM D638
Elongation at Yield	7.0 %	7.0 %	ASTM D638
Flexural Modulus	0.862 GPa	125 ksi	ASTM D790
Izod Impact, Notched	7.47 J/cm	14.0 ft-lb/in	73°F; ASTM D256

Descriptive Properties	Value	Comments
Characteristics	Antistatic, Nucleating agent	
Forms	Pellets	
Processing Methods	Injection molding	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China