

M. Holland Company IS325 Polystyrene, High Impact (discontinued **)

Category : Polymer , Thermoplastic , Polystyrene (PS) , Polystyrene, Impact Modified

Material Notes:

Features: Impact Modified Uses: Construction Applications, Structural Foam, Packaging Approvals: FDA 21 CFR 177.1520 Processing

Method: Injection Molding Information provided by M. Holland.

Order this product through the following link:

http://www.lookpolymers.com/polymer_M-Holland-Company-IS325-Polystyrene-High-Impact-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in ³	ASTM D792
Melt Flow	8.0 g/10 min @Load 5.00 kg, Temperature 200 °C	8.0 g/10 min @Load 11.0 lb, Temperature 392 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	22.1 MPa	3200 psi	Type I; ASTM D638
Elongation at Break	50 %	50 %	Type I; ASTM D638
Flexural Strength	44.1 MPa	6400 psi	at 10 in/min; ASTM D790
Flexural Modulus	2.28 GPa	330 ksi	at 10 in/min; ASTM D790
Izod Impact, Notched	1.07 J/cm	2.00 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	79.4 °C	175 °F	Unannealed; ASTM D648

Descriptive Properties	Value	Comments
Form	Pellets	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China