

M. Holland Company LD219AA LDPE (discontinued **)

Category : Polymer , Thermoplastic , Polyethylene (PE) , LDPE , Low Density Polyethylene (LDPE), Blow Molding Grade

Material Notes:

Features: Good Processability, Ultra High Toughness
Uses: Bottles, Packaging
Processing Method: Blow Molding
Information provided by M. Holland.

Order this product through the following link:

http://www.lookpolymers.com/polymer_M-Holland-Company-LD219AA-LDPE-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.919 g/cc	0.0332 lb/in ³	ASTM D1505
Melt Flow	2.3 g/10 min @Load 2.16 kg, Temperature 190 °C	2.3 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	17.9 MPa	2600 psi	ASTM D882
Elongation at Yield	350 %	350 %	ASTM D882
Flexural Modulus	0.152 GPa	22.0 ksi	1% Secant; ASTM D882

Descriptive Properties	Value	Comments
Form	Pellets	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China