

M. Holland Company MAGMA® LM112-K LLDPE (discontinued **)

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , LLDPE , Linear Low Density Polyethylene (LLDPE), Rotational Molding Grade

Material Notes:

Features: Good Heat Seal, Good Processability, Good Tear Strength, Good Toughness
 Processing Method: Extrusion
 Information provided by M. Holland.

Order this product through the following link:

http://www.lookpolymers.com/polymer_M-Holland-Company-MAGMA-LM112-K-LLDPE-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.913 g/cc	0.0330 lb/in ³	ASTM D1505
Thickness	31.8 microns	1.25 mil	
Melt Flow	1.0 g/10 min	1.0 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Film Elongation at Break, MD	520 %	520 %	ASTM D882
Film Elongation at Break, TD	710 %	710 %	ASTM D882
Elmendorf Tear Strength MD	390 g	390 g	ASTM D1922
Elmendorf Tear Strength TD	750 g	750 g	ASTM D1922
Dart Drop Test	380 g	0.838 lb	ASTM D1709
Film Tensile Strength at Break, MD	36.9 MPa	5350 psi	ASTM D882
Film Tensile Strength at Break, TD	19.3 MPa	2800 psi	ASTM D882

Thermal Properties	Metric	English	Comments
Melting Point	104 °C	220 °F	

Processing Properties	Metric	English	Comments
Feed Temperature	<= 149 °C	<= 300 °F	
Zone 1	149 °C	300 °F	
Melt Temperature	182 - 232 °C	360 - 450 °F	
Die Opening	0.0810 - 0.254 cm	0.0319 - 0.100 in	
Blow-up Ratio (BUR)	1.5 - 3.0	1.5 - 3.0	

Descriptive Properties	Value	Comments
Form	Pellets	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China