

## MTI ThermoStran<sup>®</sup> PP-40G Long Glass Fiber Compound

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 40% Glass Fiber Filler

### Material Notes:

ThermoStran<sup>®</sup> is custom designed long fiber thermoplastic compound (LFC) engineered to meet specific end use requirements. Continuous fibers are pultruded to yield pellets with fibers equivalent to the pellet length. Fiber / pellet length = 0.5 inches. Properties reported are dry as molded. Processing information: Mold Temperature: Higher mold temperatures are recommended for smoother surface appearance. Nozzle: Shortest length possible and 0.25 inch diameter or larger is recommended. Gates: Gates should be as large as possible and located to eliminate knit line and advantageously align fiber. Runners: Full round runners with 0.25 inch diameter and no sharp corners. Construction Material: Tool steels can be heat treated and polished to increase hardness and wear resistance. A-2 and D-2 steels can be hardened to Rockwell 60 C scale for longer life. Plating: Electroless nickel plating may offer additional wear protection. Information provided by MTI Thermoplastic Composites, Division of Montsinger Technologies, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_MTI-ThermoStran-PP-40G-Long-Glass-Fiber-Compound.php](http://www.lookpolymers.com/polymer_MTI-ThermoStran-PP-40G-Long-Glass-Fiber-Compound.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.21 g/cc	1.21 g/cc	
Filler Content	40 %	40 %	Long Glass Fiber

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	107 MPa	15500 psi	
Tensile Modulus	8.27 GPa	1200 ksi	
Flexural Strength	152 MPa	22000 psi	
Flexural Modulus	7.58 GPa	1100 ksi	
Izod Impact, Notched	2.72 J/cm	5.10 ft-lb/in	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	157 Â°C	315 Â°F	

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	227 Â°C	440 Â°F	
Middle Barrel Temperature	238 Â°C	460 Â°F	
Front Barrel Temperature	249 Â°C	480 Â°F	
Nozzle Temperature	249 Â°C	480 Â°F	

Melt Temperature Processing Properties	249 - 260 Å°C Metric	480 - 500 Å°F English	Comments
Mold Temperature	65.6 Å°C	150 Å°F	
Injection Pressure	68.9 MPa	10000 psi	
Screw Speed	50 - 75 rpm	50 - 75 rpm	

Descriptive Properties	Value	Comments
Nozzle ID	0.25 Inches	
Screw Design	20:1 L/D	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China