

MTM Plastics Dipolen® PP Recycled PP

Category : Polymer , Renewable/Recycled Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

Dipolen® PP is a granulated polypropylene for use in either extrusion or injection molding. It can be supplied unmodified or treated with additives according to customer specifications. Dipolen® boasts a high level of polyolefin purity, through an extremely selective recycling technology, and through thorough degassing and very fine filtration. Various colors are available. Information provided by MTM Plastics GmbH.

Order this product through the following link:

http://www.lookpolymers.com/polymer_MTM-Plastics-Dipolen-PP-Recycled-PP.php

Physical Properties	Metric	English	Comments
Density	0.916 g/cc	0.0331 lb/in ³	ISO 1183
Moisture Absorption	<= 0.100 %	<= 0.100 %	
Melt Flow	>= 10 g/10 min	>= 10 g/10 min	ISO 1133
	@Load 2.16 kg, Temperature 230 °C	@Load 4.76 lb, Temperature 446 °F	
Melt Flow	>= 24 g/10 min	>= 24 g/10 min	
	@Load 5.00 kg, Temperature 190 °C	@Load 11.0 lb, Temperature 374 °F	
Ash	<= 2.0 %	<= 2.0 %	Ignition Residue after 650°C; ISO 1172

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	61	61	DIN 53505
Tensile Strength, Yield	>= 24.0 MPa	>= 3480 psi	50 mm/min; ISO 527
Elongation at Yield	>= 18 %	>= 18 %	50 mm/min; ISO 527
Tensile Modulus	>= 1.10 GPa	>= 160 ksi	1 mm/min; ISO 527
Charpy Impact, Notched	>= 0.300 J/cm ²	>= 1.43 ft-lb/in ²	edgewise; ISO 179
	@Temperature -23.0 °C	@Temperature -9.40 °F	
Charpy Impact, Notched	>= 0.650 J/cm ²	>= 3.09 ft-lb/in ²	edgewise; ISO 179
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China