

Mallard Creek Polymers ROVENE® 6020 SBR Latex

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Styrene Butadiene Rubber

Material Notes:

Applications: Rovene® 6020 is a soft, carboxylated styrene-acrylic copolymer emulsion. The typical films are soft and strong with good water resistance and exhibit good resistance to discoloration. This emulsion has found typical applications are coatings for awnings, boat covers, gloss overprints for fabric and outdoor casual furniture upholstery. **Storage and Handling:** Protect from freezing. Ideal storage temperature is 22°C (72°F). Read the Rovene® 6020 Material Safety Data Sheet before handling, storing, or using this product. Information provided by Mallard Creek Polymers

Order this product through the following link:

http://www.lookpolymers.com/polymer_Mallard-Creek-Polymers-ROVENE-6020-SBR-Latex.php

Physical Properties	Metric	English	Comments
Solids Content	48.5 - 49.5 %	48.5 - 49.5 %	
Particle Size	0.15 µm	0.15 µm	
pH	3.0 - 5.0	3.0 - 5.0	
Brookfield Viscosity	700 cP	700 cP	#2/20 rpm

Thermal Properties	Metric	English	Comments
Glass Transition Temp, Tg	-17.0 °C	1.40 °F	

Descriptive Properties	Value	Comments
Emulsifiers	Anionic	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China