

## Mallard Creek Polymers Rovene® 4045 Styrene-Butadiene Emulsion

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Styrene Butadiene Rubber

### Material Notes:

Description: Rovene® 4045 is recommended in applications where soil and aggregate stabilization and binding are required. Rovene® 4045 can be used in the process of road construction, landscaping, agriculture and erosion control applications. It provides good wetting of various soil types, imparts dry and wet strength to the soil and aggregates, and provides dust control. Storage and Handling: Protect from freezing. Ideal storage temperature is 22°C (72°F). Read the Rovene® 4045 Material Safety Data Sheet before handling, storing, or using this product. Information provided by Mallard Creek Polymers

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Mallard-Creek-Polymers-Rovene-4045-Styrene-Butadiene-Emulsion.php](http://www.lookpolymers.com/polymer_Mallard-Creek-Polymers-Rovene-4045-Styrene-Butadiene-Emulsion.php)

Physical Properties	Metric	English	Comments
Solids Content	45 - 45.7 %	45 - 45.7 %	
pH	7.8 - 8.4	7.8 - 8.4	
Brookfield Viscosity	<= 900 cP	<= 900 cP	#20/200

Thermal Properties	Metric	English	Comments
Glass Transition Temp, Tg	24.0 Å°C	75.2 Å°F	

Descriptive Properties	Value	Comments
Emulsifiers	Anionic	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China