

Mallard Creek Polymers Rovene® 4125 Styrene-Butadiene Emulsion

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Styrene Butadiene Rubber

Material Notes:

Applications: Rovene® 4125 is recommended for applications where a primer-sealer that provides adhesion between asphalt and other various surface treatments is needed. Rovene® 4125 has been used in recreational surface applications such as tennis court and running track coatings. Storage and Handling: Protect from freezing. Ideal storage temperature is 22°C (72°F). Read the Rovene® 4125 Material Safety Data Sheet before handling, storing, or using this product. Information provided by Mallard Creek Polymers

Order this product through the following link:

http://www.lookpolymers.com/polymer_Mallard-Creek-Polymers-Rovene-4125-Styrene-Butadiene-Emulsion.php

| Physical Properties | Metric | English | Comments |
|----------------------|-------------|-------------|----------|
| Solids Content | 49 - 51.5 % | 49 - 51.5 % | |
| Particle Size | 0.19 µm | 0.19 µm | |
| pH | 8.5 - 10 | 8.5 - 10 | |
| Brookfield Viscosity | 75 - 500 cP | 75 - 500 cP | #20/200 |

| Thermal Properties | Metric | English | Comments |
|---------------------------|----------|----------|----------|
| Glass Transition Temp, Tg | -27.0 °C | -16.6 °F | |

| Descriptive Properties | Value | Comments |
|------------------------|---------|----------|
| Emulsifiers | Anionic | |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China