

Mallard Creek Polymers Rovene® 4560 Styrene-Butadiene Emulsion

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Styrene Butadiene Rubber

Material Notes:

Description: ROVENE® 4560 is an anionic carboxylated styrene-butadiene copolymer latex designed for fast film formation and excellent water resistance. Features: Highly stable Cured films are tough and flexible across a broad range of temperatures Cured films have excellent water resistance Hydrolysis resistant Filler compatible Applications: ROVENE® 4560 is a general purpose latex binder of low stiffness. It dries to form a soft but tough film. Its softness makes it excellent for applications requiring flexibility, adhesion, and excellent water resistance. Storage and Handling: Protect from freezing. Ideal storage temperature is 22°C (72°F). Stability at 22°C (72°F) is 180 days when properly stored. Read the BarrierPro® 4560 Material Safety Data Sheet before handling, storing, or using this product. Information provided by Mallard Creek Polymers

Order this product through the following link:

http://www.lookpolymers.com/polymer_Mallard-Creek-Polymers-Rovene-4560-Styrene-Butadiene-Emulsion.php

Physical Properties	Metric	English	Comments
Volatiles	48 - 50 %	48 - 50 %	
pH	8.0 - 8.5	8.0 - 8.5	

Thermal Properties	Metric	English	Comments
Glass Transition Temp, Tg	-17.0 °C	1.40 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China