

## Mallard Creek Polymers Rovene® 6015 Acrylic Emulsion

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

**Applications:** Rovene® 6015 is a self crosslinking acrylic polymer providing a medium hand to frothed or saturated substrates. Rovene® 6015 is recommended for various nonwoven and paper applications requiring medium hand with resistance to heat and light aging. Rovene® 6015 also provides good wet strength and chemical resistance.  
**Storage and Handling:** Protect from freezing. Ideal storage temperature is 22°C (72°F). Read the Rovene® 6015 Material Safety Data Sheet before handling, storing, or using this product.  
Information provided by Mallard Creek Polymers

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Mallard-Creek-Polymers-Rovene-6015-Acrylic-Emulsion.php](http://www.lookpolymers.com/polymer_Mallard-Creek-Polymers-Rovene-6015-Acrylic-Emulsion.php)

Physical Properties	Metric	English	Comments
Solids Content	48 - 50 %	48 - 50 %	
Particle Size	0.19 µm	0.19 µm	
pH	3.0 - 5.0	3.0 - 5.0	
Brookfield Viscosity	<= 600 cP	<= 600 cP	#20/200

Thermal Properties	Metric	English	Comments
Glass Transition Temp, Tg	-8.00 °C	17.6 °F	

Descriptive Properties	Value	Comments
Emulsifiers	Anionic	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China