

Mallard Creek Polymers Rovene® 6119 Styrene-Acrylic Emulsion

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Applications: Rovene® 6119 is a low glass transition temperature styrene-acrylic polymer that offers flexibility during movement of the substrate and water resistance. Rovene® 6119 also exhibits excellent tensile strength and maintains elongation properties when compounded with fillers.
Storage and Handling: Protect from freezing. Ideal storage temperature is 22°C (72°F). Read the Rovene® 6119 Material Safety Data Sheet before handling, storing, or using this product. Information provided by Mallard Creek Polymers

Order this product through the following link:

http://www.lookpolymers.com/polymer_Mallard-Creek-Polymers-Rovene-6119-Styrene-Acrylic-Emulsion.php

Physical Properties	Metric	English	Comments
Solids Content	51.5 - 52.5 %	51.5 - 52.5 %	
Particle Size	0.20 µm	0.20 µm	
pH	8.5 - 9.5	8.5 - 9.5	
Brookfield Viscosity	<= 500 cP	<= 500 cP	#20/200

Thermal Properties	Metric	English	Comments
Glass Transition Temp, Tg	-24.0 °C	-11.2 °F	

Descriptive Properties	Value	Comments
Emulsifiers	Anionic	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China