

## Mallard Creek Polymers Rovene® 6126 Styrene-Acrylic Emulsion

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

Applications: Rovene® 6126 provides a flexible yet strong cohesive bond for a range of materials and particle surface areas. Rovene® 6126 imparts films with good water resistance properties. For use in the following application areas: Quarries Mines (particularly coal) Stockpiles Landfills Unpaved Roads Material/Mineral Transport Storage and Handling: Protect from freezing. Ideal storage temperature is 22°C (72°F). Read the Rovene® 6126 Material Safety Data Sheet before handling, storing, or using this product. Information provided by Mallard Creek Polymers

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Mallard-Creek-Polymers-Rovene-6126-Styrene-Acrylic-Emulsion.php](http://www.lookpolymers.com/polymer_Mallard-Creek-Polymers-Rovene-6126-Styrene-Acrylic-Emulsion.php)

Physical Properties	Metric	English	Comments
Solids Content	39.5 - 40.5 %	39.5 - 40.5 %	
Particle Size	0.18 µm	0.18 µm	
pH	4.0 - 5.0	4.0 - 5.0	
Brookfield Viscosity	<= 500 cP	<= 500 cP	#20/200

Thermal Properties	Metric	English	Comments
Glass Transition Temp, Tg	20.0 °C	68.0 °F	

Descriptive Properties	Value	Comments
Emulsifiers	Anionic	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China