

Malvern Minerals Novakup® L-207A Surface-Treated Lamellar Quartz Filler/Extender

Category: Ceramic, Oxide, Silicon Oxide, Other Engineering Material, Additive/Filler for Polymer

Material Notes:

Novakup® is a surface modified or silane treated Novacite®. It has been used its barrier prosperities in chemical and corrosion resistant applications and as a filler/extender/reinforcing agent in polymers. Novacite® quartz silica has closely controlled sizing that is used extensively in the coatings field. Novacite® has broad acceptance as silica in special purpose, product finishes OEM, automotive and industrial coatings. The unique, disc-like or lamellar shape of Novacite® makes it useful for coating systems where low oil absorption and improved barrier properties are desired. In coatings, the lamellar plate overlap parallel to the substrate surface. It has a polar, wettable surface and is very transparent in the UV and visible range. Its structure alpha (low) quartz, which is stable to 573°C. The crystallography of Novacite shows it is an uncommon variety of quartz, with anhedral or subhedral crystals that cleave along the principal axis of the molecular structure. Information provided by Malvern Minerals Company.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Malvern-Minerals-Novakup-L-207A-Surface-Treated-Lamellar-Quartz-FillerExtender.php

| Physical Properties | Metric | English | Comments |
|---------------------|---|---|---------------|
| Specific Gravity | 2.65 g/cc | 2.65 g/cc | |
| Bulk Density | 0.8486 g/cc | 0.03065 lb/in³ | Loose packed |
| | 1.326 g/cc | 0.04789 lb/in³ | Dense Packed |
| Brightness | 80 % | 80 % | GE Brightness |
| Oil Absorption | 17 - 20 % | 17 - 20 % | |
| Fineness | 6.0 - 7.0 | 6.0 - 7.0 | Hegman |
| Water Absorption | 8.7 % | 8.7 % | |
| | 0.00 % | 0.00 % | |
| | @Temperature 110 °C, Time 10800 sec | @Temperature 230 °F, Time 3.00 hour | |
| | 0.00 % | 0.00 % | |
| | @Temperature 1000 °C, Time 1800 sec | @Temperature 1830 °F, Time 0.500 hour | |
| Porosity | 0.48 - 0.52 % | 0.48 - 0.52 % | |
| Particle Size | >= 2.0 Âμm | >= 2.0 Âμm | 2% finer |
| | 3.0 - 5.0 Âμm | 3.0 - 5.0 Âμm | average |
| | <= 10 Âμm | <= 10 Âμm | 99% finer |
| | | | |



| Physical Properties | 6.0 - 6.3 Metric | 6 0 - 6 3 English | in distilled water Comments |
|-----------------------|---------------------|----------------------|--------------------------------|
| Mechanical Properties | Metric | English | Comments |
| Knoop Microhardness | 820 | 820 | |
| Hardness, Mohs | 7.0 | 7.0 | |

| Thermal Properties | Metric | English | Comments |
|----------------------------|-----------------------------|-------------------------------|--|
| Specific Heat Capacity | 0.803 J/g-°C | 0.192 BTU/lb-°F | Typical Novacite; finer grades are lower than coarser grades |
| | @Temperature 0.000 - 200 °C | @Temperature 32.0 - 392 °F | |
| Transformation Temperature | 573.7 °C | 1065 °F | on heating |
| | 573.8 °C | 1065 °F | on cooling |

| Optical Properties | Metric | English | Comments | |
|--------------------|--------|---------|----------|--|
| Refractive Index | 1.550 | 1.550 | | |

| Component Elements Properties | Metric | English | Comments |
|-------------------------------|---------|---------|----------|
| Al203 | 0.102 % | 0.102 % | |
| CaO | 0.014% | 0.014 % | |
| Fe2O3 | 0.039 % | 0.039 % | |
| Loss on Ignition(%) | 0.19 % | 0.19 % | |
| MgO | 0.021 % | 0.021 % | |
| SiO2 | 99.49 % | 99.49 % | |
| TiO2 | 0.015 % | 0.015 % | |

| Descriptive Properties | Value | Comments |
|------------------------|----------|----------|
| Acid Number | 0 | 0-18 |
| Color | Gray-Tan | Wet |
| | White | Dry |

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com



Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China