

MarkeTech 93-4-3 Tungsten Alloy, AMS-T-21014 Class 2

Category : Metal , Nonferrous Metal , Refractory Metal , Tungsten Alloy

Material Notes:

Used to fabricate parts to near net size and several processes to produce high quality tungsten based materials. Tungsten heavy alloys have very high melting point and have a density twice that of steel and are more than 50% heavier than lead. Due to their high density, tungsten alloys offer greater radiation shielding than lead and are non-toxic. Tungsten alloys are electrically and thermal conductive and offer good corrosion resistance. They also have a low coefficient of expansion and have a high modulus of elasticity. Because of these unique properties tungsten alloys are used extensively in military applications, balance weights, aircraft components, nuclear and medical shields, fishing and sport tackle, rocket components, tool vibration dampers, electrical contacts, etc. Applications: Nuclear and medical radiation shielding for x-ray and shields for radiation therapy and industrial applications. Aircraft and helicopter rotor balance weights Instrument balance weights Weights for sport equipment Tool damping cutter bars High voltage contacts Information provided by MarkeTech International.

Order this product through the following link:

http://www.lookpolymers.com/polymer_MarkeTech-93-4-3-Tungsten-Alloy-AMS-T-21014-Class-2.php

Physical Properties	Metric	English	Comments
Density	17.6 g/cc	0.636 lb/in ³	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell C	26 - 30	26 - 30	Sintered Only
	35 - 45	35 - 45	Swaged after Sintering
Tensile Strength, Ultimate	900 - 1100 MPa	131000 - 160000 psi	Sintered Only
	1150 - 1250 MPa	167000 - 181000 psi	ASwaged after Sintering
Tensile Strength, Yield	900 - 1100 MPa	131000 - 160000 psi	Swaged after Sintering
	7.0 - 18 %	7.0 - 18 %	Swaged after Sintering
Elongation at Break	16 - 24 %	16 - 24 %	Sintered Only
	30	30	J/cm ² ; Swaged after Sintering
Impact	90	90	J/cm ² ; Sintered Only

Component Elements Properties	Metric	English	Comments
Iron, Fe	3 %	3 %	
Nickel, Ni	4 %	4 %	
Tungsten, W	93 %	93 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China