

MarkeTech Repton 201 Aluminum Oxide

Category: Ceramic, Oxide, Aluminum Oxide

Material Notes:

REPTON setter tiles, kiln furniture, and special fixtures are lightweight, ridge, and high strength ceramics that resist distortion and spalling, even when thermal cycled many times. They are available with a smooth or a unique textured surface that permits pinpoint contact with the load. Sticking can be eliminated as well as providing a surface that breathes, allowing gasses from the ceramic to escape. Applications include firing ceramic capacitors, SOFCs, PZTs, hard and soft ferrites, co-fired substrates and powdered metals. REPTON is available in a wide range of compositions that include a range of alumina, mullite/alumina, zirconia, cordierite, magnesia, and aluminum titanate.

Order this product through the following link:

http://www.lookpolymers.com/polymer_MarkeTech-Repton-201-Aluminum-Oxide.php

| Physical Properties | Metric | English | Comments |
|---------------------|-----------|---------------|--|
| Bulk Density | 1.50 g/cc | 0.0542 lb/in³ | |
| Density | 4.05 g/cc | 0.146 lb/in³ | calculated from bulk density after subtracting pore volume |
| Porosity | 63 % | 63 % | |

| Mechanical Properties | Metric | English | Comments |
|-----------------------|-------------|-------------|----------|
| Flexural Strength | >= 7.00 MPa | >= 1020 psi | |

| Component Elements Properties | Metric | English | Comments | |
|-------------------------------|--------|---------|----------|--|
| Al203 | 99.6 % | 99.6 % | | |

| Descriptive Properties | Value | Comments |
|------------------------|-------|----------|
| Spall Resist | 400°C | |

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China