

## MarkeTech Repton 504 Mullite

Category : Ceramic , Oxide , Aluminum Oxide

### Material Notes:

Brand 504 features: Max spall resistance. REPTON setter tiles, kiln furniture, and special fixtures are lightweight, ridge, and high strength ceramics that resist distortion and spalling, even when thermal cycled many times. They are available with a smooth or a unique textured surface that permits pinpoint contact with the load. Sticking can be eliminated as well as providing a surface that breathes, allowing gasses from the ceramic to escape. Applications include firing ceramic capacitors, SOFCs, PZTs, hard and soft ferrites, co-fired substrates and powdered metals. REPTON is available in a wide range of compositions that include a range of alumina, mullite/alumina, zirconia, cordierite, magnesia, and aluminum titanate.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_MarkeTech-Repton-504-Mullite.php](http://www.lookpolymers.com/polymer_MarkeTech-Repton-504-Mullite.php)

Physical Properties	Metric	English	Comments
Bulk Density	2.50 g/cc	0.0903 lb/in <sup>3</sup>	
Density	3.68 g/cc	0.133 lb/in <sup>3</sup>	calculated from bulk density after subtracting pore volume
Porosity	32 %	32 %	

Mechanical Properties	Metric	English	Comments
Flexural Strength	>= 7.00 MPa	>= 1020 psi	

Thermal Properties	Metric	English	Comments
CTE, linear	3.90 $\mu\text{m/m-}^{\circ}\text{C}$	2.17 $\mu\text{in/in-}^{\circ}\text{F}$	
	@Temperature 300 $^{\circ}\text{C}$	@Temperature 572 $^{\circ}\text{F}$	
	5.00 $\mu\text{m/m-}^{\circ}\text{C}$	2.78 $\mu\text{in/in-}^{\circ}\text{F}$	
	@Temperature 900 $^{\circ}\text{C}$	@Temperature 1650 $^{\circ}\text{F}$	

Component Elements Properties	Metric	English	Comments
Al <sub>2</sub> O <sub>3</sub>	90 %	90 %	
SiO <sub>2</sub>	10 %	10 %	

Descriptive Properties	Value	Comments
Spall Resist	650 $^{\circ}\text{C}$	

Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China