

## MarkeTech Repton EXP 386 Aluminum Titanate

Category : Ceramic , Oxide , Aluminum Oxide

**Material Notes:**

REPTON setter tiles, kiln furniture, and special fixtures are lightweight, ridge, and high strength ceramics that resist distortion and spalling, even when thermal cycled many times. They are available with a smooth or a unique textured surface that permits pinpoint contact with the load. Sticking can be eliminated as well as providing a surface that breathes, allowing gasses from the ceramic to escape. Applications include firing ceramic capacitors, SOFCs, PZTs, hard and soft ferrites, co-fired substrates and powdered metals. REPTON is available in a wide range of compositions that include a range of alumina, mullite/alumina, zirconia, cordierite, magnesia, and aluminum titanate.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_MarkeTech-Repton-EXP-386-Aluminum-Titanate.php](http://www.lookpolymers.com/polymer_MarkeTech-Repton-EXP-386-Aluminum-Titanate.php)

Physical Properties	Metric	English	Comments
Bulk Density	2.70 g/cc	0.0975 lb/in <sup>3</sup>	
Density	3.14 g/cc	0.113 lb/in <sup>3</sup>	calculated from bulk density after subtracting pore volume
Porosity	14 %	14 %	

Mechanical Properties	Metric	English	Comments
Flexural Strength	>= 25.0 MPa	>= 3630 psi	

Thermal Properties	Metric	English	Comments
CTE, linear	0.000 $\mu\text{m/m-}^\circ\text{C}$	0.000 $\mu\text{in/in-}^\circ\text{F}$	
	@Temperature 300 $^\circ\text{C}$	@Temperature 572 $^\circ\text{F}$	
	1.70 $\mu\text{m/m-}^\circ\text{C}$	0.944 $\mu\text{in/in-}^\circ\text{F}$	
	@Temperature 900 $^\circ\text{C}$	@Temperature 1650 $^\circ\text{F}$	

Descriptive Properties	Value	Comments
Spall Resist	1000 $^\circ\text{C}$	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China