

Materion AlBeMet® AM 162 Rolled Sheet, Annealed

Category : Metal , Metal Matrix Composite , Nonferrous Metal , Beryllium Alloy

Material Notes:

Mechanical properties are typical, longitudinal values at RT. AlBeMet® AM 162 is a powder metallurgical product produced by gas atomization available as rod, bar, tube and sheet. These shapes are derived by consolidating the Al/Be powder by hot isostatic pressing (HIP) and cold isostatic pressing (CIP) followed by extrusion or sheet rolling processes. Used for heat sinks and structural parts in aircraft and satellite avionics because of its low density, high modulus, high thermal conductivity, low CTE, and thermal stability. Please note that there are health hazards associated with beryllium, especially when present as airborne particles generated during processing. As with any material, be aware of hazards and take steps to reduce exposure to a safe level. Information provided by Brush Wellman. Brush Engineered Materials Inc. changed its name to Materion Corporation in March 2011.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Materion-AlBeMet-AM-162-Rolled-Sheet-Annealed.php

Physical Properties	Metric	English	Comments
Density	2.071 g/cc	0.07482 lb/in ³	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell B	68	68	
Tensile Strength, Ultimate	>= 379 MPa	>= 55000 psi	Minimum
	435 MPa	63100 psi	Typical
Tensile Strength, Yield	>= 276 MPa	>= 40000 psi	Minimum
	321 MPa	46600 psi	Typical
Elongation at Break	>= 5.0 %	>= 5.0 %	Minimum
	9.0 %	9.0 %	Typical
Modulus of Elasticity	193 GPa	28000 ksi	
Poissons Ratio	0.17	0.17	
Shear Modulus	82.0 GPa	11900 ksi	calculated

Thermal Properties	Metric	English	Comments
CTE, linear	13.91 µm/m-°C	7.728 µin/in-°F	
	@Temperature 25.0 °C	@Temperature 77.0 °F	
Specific Heat Capacity	1.56 J/g-°C	0.373 BTU/lb-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	

Thermal Properties	Metric	English	Comments
Melting Point	644 - 1082 °C	1190 - 1980 °F	
Solidus	644 °C	1190 °F	
Liquidus	1082 °C	1980 °F	

Component Elements Properties	Metric	English	Comments
Aluminum, Al	38 %	38 %	As remainder
Beryllium, Be	60 - 64 %	60 - 64 %	
Carbon, C	0.00 - 0.10 %	0.00 - 0.10 %	
Other, each	0.00 - 0.20 %	0.00 - 0.20 %	
Oxygen, O	0.00 - 1.0 %	0.00 - 1.0 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.00000350 ohm-cm @Temperature 20.0 °C	0.00000350 ohm-cm @Temperature 68.0 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China