

## Materion Beryllium Copper Alloy 10 Plate & Rolled Bar; H (TD04) Temper; up to 76 mm Thickness (UNS C17500)

Category : Metal , Nonferrous Metal , Beryllium Alloy , Copper Alloy

### Material Notes:

Treatment required for max strength: as supplied  
Tabulated properties apply to products after age hardening. Information supplied by Brush Wellman. Brush Engineered Materials Inc. changed its name to Materion Corporation in March 2011.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Materion-Beryllium-Copper-Alloy-10-Plate-Rolled-Bar-H-TD04-Temper-up-to-76-mm-Thickness-UNS-C17500.php](http://www.lookpolymers.com/polymer_Materion-Beryllium-Copper-Alloy-10-Plate-Rolled-Bar-H-TD04-Temper-up-to-76-mm-Thickness-UNS-C17500.php)

Physical Properties	Metric	English	Comments
Density	8.83 g/cc	0.319 lb/in <sup>3</sup>	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell B	78 - 88	78 - 88	
Tensile Strength, Ultimate	480 - 590 MPa	69600 - 85600 psi	
Tensile Strength, Yield	370 - 560 MPa	53700 - 81200 psi	
Elongation at Break	2.0 - 8.0 %	2.0 - 8.0 %	
Modulus of Elasticity	138 GPa	20000 ksi	
Machinability	40 %	40 %	

Thermal Properties	Metric	English	Comments
CTE, linear	18.0 $\mu\text{m/m}\cdot\text{Å}^\circ\text{C}$ @Temperature 20.0 - 200 $\text{Å}^\circ\text{C}$	10.0 $\mu\text{in/in}\cdot\text{Å}^\circ\text{F}$ @Temperature 68.0 - 392 $\text{Å}^\circ\text{F}$	
Thermal Conductivity	240 W/m-K	1670 BTU-in/hr-ft <sup>2</sup> - $\text{Å}^\circ\text{F}$	
Melting Point	1010 - 1050 $\text{Å}^\circ\text{C}$	1850 - 1920 $\text{Å}^\circ\text{F}$	
Solidus	1010 $\text{Å}^\circ\text{C}$	1850 $\text{Å}^\circ\text{F}$	
Liquidus	1050 $\text{Å}^\circ\text{C}$	1920 $\text{Å}^\circ\text{F}$	

Component Elements Properties	Metric	English	Comments
Beryllium, Be	0.40 - 0.70 %	0.40 - 0.70 %	
Cobalt, Co	2.4 - 2.7 %	2.4 - 2.7 %	

Component Elements Properties	Metric	English	Comments
Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.00000570 - 0.00000860 ohm-cm	0.00000570 - 0.00000860 ohm-cm	20-30% IACS Conductivity

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China