

Materion Beryllium Copper Alloy 10 Rod and Bar; H (TD04) Temper; up to 76 mm (UNS C17500)

Category : Metal , Nonferrous Metal , Beryllium Alloy , Copper Alloy

Material Notes:

Treatment required for max strength: as supplied
Tabulated properties apply to products after age hardening. Information supplied by Brush Wellman. Brush Engineered Materials Inc. changed its name to Materion Corporation in March 2011.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Materion-Beryllium-Copper-Alloy-10-Rod-and-Bar-H-TD04-Temper-up-to-76-mm-UNS-C17500.php

Physical Properties	Metric	English	Comments
Density	8.83 g/cc	0.319 lb/in ³	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell B	60 - 80	60 - 80	
Tensile Strength, Ultimate	440 - 560 MPa	63800 - 81200 psi	
Tensile Strength, Yield	340 - 520 MPa	49300 - 75400 psi	
Elongation at Break	10 - 15 %	10 - 15 %	
Modulus of Elasticity	138 GPa	20000 ksi	
Machinability	40 %	40 %	

Thermal Properties	Metric	English	Comments
CTE, linear	18.0 $\mu\text{m/m-}^\circ\text{C}$ @Temperature 20.0 - 200 $^\circ\text{C}$	10.0 $\mu\text{in/in-}^\circ\text{F}$ @Temperature 68.0 - 392 $^\circ\text{F}$	
Thermal Conductivity	200 W/m-K	1390 BTU-in/hr-ft ² - $^\circ\text{F}$	
Melting Point	1010 - 1050 $^\circ\text{C}$	1850 - 1920 $^\circ\text{F}$	
Solidus	1010 $^\circ\text{C}$	1850 $^\circ\text{F}$	
Liquidus	1050 $^\circ\text{C}$	1920 $^\circ\text{F}$	

Component Elements Properties	Metric	English	Comments
Beryllium, Be	0.40 - 0.70 %	0.40 - 0.70 %	
Cobalt, Co	2.4 - 2.7 %	2.4 - 2.7 %	

Component Elements Properties	Metric	English	Comments
Electrical Properties			
Electrical Resistivity	0.00000570 - 0.00000860 ohm-cm	0.00000570 - 0.00000860 ohm-cm	20-30% IACS Conductivity

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China