

## Materion Beryllium Copper Alloy 245C Castings (UNS C82600)

Category : Metal , Nonferrous Metal , Beryllium Alloy , Copper Alloy , Copper Casting Alloy

### Material Notes:

Pouring Temperature: 970-1065°C Heat treatment required for max strength (Annealing): 760-790°C/water quench Heat treatment required for max strength (Hardening): 760-790°C/water quench Tabulated properties apply to products after age hardening. Information supplied by Brush Wellman. Brush Engineered Materials Inc. changed its name to Materion Corporation in March 2011.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Materion-Beryllium-Copper-Alloy-245C-Castings-UNS-C82600.php](http://www.lookpolymers.com/polymer_Materion-Beryllium-Copper-Alloy-245C-Castings-UNS-C82600.php)

Physical Properties	Metric	English	Comments
Density	8.22 g/cc	0.297 lb/in <sup>3</sup>	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell C	40 - 45	40 - 45	
Tensile Strength, Ultimate	1140 - 1250 MPa	165000 - 181000 psi	Solution Annealed & Aged
Tensile Strength, Yield	1060 - 1170 MPa	154000 - 170000 psi	Solution Annealed & Aged
Elongation at Break	1.0 - 2.0 %	1.0 - 2.0 %	Solution Annealed & Aged
Modulus of Elasticity	131 GPa	19000 ksi	

Thermal Properties	Metric	English	Comments
CTE, linear	18.0 $\mu\text{m/m}\cdot\text{Å}^\circ\text{C}$ @Temperature 20.0 - 200 $\text{Å}^\circ\text{C}$	10.0 $\mu\text{in/in}\cdot\text{Å}^\circ\text{F}$ @Temperature 68.0 - 392 $\text{Å}^\circ\text{F}$	
Thermal Conductivity	93.0 W/m-K	645 BTU-in/hr-ft <sup>2</sup> - $\text{Å}^\circ\text{F}$	
Melting Point	860 - 955 $\text{Å}^\circ\text{C}$	1580 - 1750 $\text{Å}^\circ\text{F}$	
Solidus	860 $\text{Å}^\circ\text{C}$	1580 $\text{Å}^\circ\text{F}$	
Liquidus	955 $\text{Å}^\circ\text{C}$	1750 $\text{Å}^\circ\text{F}$	

Component Elements Properties	Metric	English	Comments
Beryllium, Be	2.25 - 2.55 %	2.25 - 2.55 %	
Carbon, C	0.20 - 0.35 %	0.20 - 0.35 %	
Cobalt, Co	0.35 - 0.65 %	0.35 - 0.65 %	
Copper, Cu	97 %	97 %	as balance

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.00000750 - 0.00000960 ohm-cm	0.00000750 - 0.00000960 ohm-cm	18-23% IACS Conductivity

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China