

Materion Beryllium Copper Alloy 25 Plate & Rolled Bar; HT (TH04) Temper; over 9.5 to 25 mm Thickness (UNS C17200)

Category : Metal , Nonferrous Metal , Beryllium Alloy , Copper Alloy

Material Notes:

Treatment required for max strength: 2 hrs @ 330°C or Mill Hardened Tabulated properties apply to products after age hardening.

Information supplied by Brush Wellman. Brush Engineered Materials Inc. changed its name to Materion Corporation in March 2011.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Materion-Beryllium-Copper-Alloy-25-Plate-Rolled-Bar-HT-TH04-Temper-over-95-to-25-mm-Thickness-UNS-C17200.php

Physical Properties	Metric	English	Comments
Density	8.36 g/cc	0.302 lb/in ³	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell C	38 - 44	38 - 44	
Tensile Strength, Ultimate	1240 - 1520 MPa	180000 - 220000 psi	
Tensile Strength, Yield	1060 - 1380 MPa	154000 - 200000 psi	
Elongation at Break	1.0 - 5.0 %	1.0 - 5.0 %	
Modulus of Elasticity	131 GPa	19000 ksi	

Thermal Properties	Metric	English	Comments
CTE, linear	17.0 $\mu\text{m/m-}^\circ\text{C}$ @Temperature 20.0 - 200 $^\circ\text{C}$	9.44 $\mu\text{in/in-}^\circ\text{F}$ @Temperature 68.0 - 392 $^\circ\text{F}$	
Thermal Conductivity	105 W/m-K	729 BTU-in/hr-ft ² - $^\circ\text{F}$	
Melting Point	870 - 980 $^\circ\text{C}$	1600 - 1800 $^\circ\text{F}$	
Solidus	870 $^\circ\text{C}$	1600 $^\circ\text{F}$	
Liquidus	980 $^\circ\text{C}$	1800 $^\circ\text{F}$	

Component Elements Properties	Metric	English	Comments
Beryllium, Be	1.8 - 2.0 %	1.8 - 2.0 %	
Co + Ni	≥ 0.20 %	≥ 0.20 %	
Co + Ni + Fe	≤ 0.60 %	≤ 0.60 %	
Copper, Cu			as balance

Component Elements Properties	98 % Metric	98 % English	Comments
Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.00000610 - 0.00000780 ohm-cm	0.00000610 - 0.00000780 ohm-cm	22-28% IACS Conductivity

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China