

## Materion Beryllium Copper Alloy 3 Wire; A (TB00) Temper; 1.3-12.7 mm Diameter (UNS C17510)

Category : Metal , Nonferrous Metal , Beryllium Alloy , Copper Alloy

### Material Notes:

Treatment required for max strength: as supplied  
Tabulated properties apply to products after age hardening. Information supplied by Brush Wellman. Brush Engineered Materials Inc. changed its name to Materion Corporation in March 2011.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Materion-Beryllium-Copper-Alloy-3-Wire-A-TB00-Temper-13-127-mm-Diameter-UNS-C17510.php](http://www.lookpolymers.com/polymer_Materion-Beryllium-Copper-Alloy-3-Wire-A-TB00-Temper-13-127-mm-Diameter-UNS-C17510.php)

Physical Properties	Metric	English	Comments
Density	8.83 g/cc	0.319 lb/in <sup>3</sup>	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	240 - 380 MPa	34800 - 55100 psi	
Tensile Strength, Yield	60.0 - 210 MPa	8700 - 30500 psi	
Elongation at Break	20 - 60 %	20 - 60 %	
Modulus of Elasticity	138 GPa	20000 ksi	
Machinability	40 %	40 %	

Thermal Properties	Metric	English	Comments
CTE, linear	18.0 $\mu\text{m/m}\cdot\text{Å}^\circ\text{C}$ @Temperature 20.0 - 200 $\text{Å}^\circ\text{C}$	10.0 $\mu\text{in/in}\cdot\text{Å}^\circ\text{F}$ @Temperature 68.0 - 392 $\text{Å}^\circ\text{F}$	
Thermal Conductivity	240 W/m-K	1670 BTU-in/hr-ft <sup>2</sup> - $\text{Å}^\circ\text{F}$	
Melting Point	1040 - 1080 $\text{Å}^\circ\text{C}$	1900 - 1980 $\text{Å}^\circ\text{F}$	
Solidus	1040 $\text{Å}^\circ\text{C}$	1900 $\text{Å}^\circ\text{F}$	
Liquidus	1080 $\text{Å}^\circ\text{C}$	1980 $\text{Å}^\circ\text{F}$	

Component Elements Properties	Metric	English	Comments
Beryllium, Be	0.20 - 0.60 %	0.20 - 0.60 %	
Copper, Cu	98 %	98 %	as balance
Nickel, Ni	1.4 - 2.2 %	1.4 - 2.2 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.00000570 - 0.00000860 ohm-cm	0.00000570 - 0.00000860 ohm-cm	20-30% IACS Conductivity

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China