

Materion Beryllium Copper Alloy 3 Wire; AT (TF00) Temper; 1.3-12.7 mm Diameter (UNS C17510)

Category : Metal , Nonferrous Metal , Beryllium Alloy , Copper Alloy

Material Notes:

Treatment required for max strength: 3 hrs @ 480-495°C or Mill Hardened Tabulated properties apply to products after age hardening.

Information supplied by Brush Wellman. Brush Engineered Materials Inc. changed its name to Materion Corporation in March 2011.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Materion-Beryllium-Copper-Alloy-3-Wire-AT-TF00-Temper-13-127-mm-Diameter-UNS-C17510.php

Physical Properties	Metric	English	Comments
Density	8.83 g/cc	0.319 lb/in ³	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	680 - 900 MPa	98600 - 131000 psi	
Tensile Strength, Yield	550 - 760 MPa	79800 - 110000 psi	
Elongation at Break	>= 10 %	>= 10 %	
Modulus of Elasticity	138 GPa	20000 ksi	

Thermal Properties	Metric	English	Comments
CTE, linear	18.0 µm/m-°C	10.0 µin/in-°F	
	@Temperature 20.0 - 200 °C	@Temperature 68.0 - 392 °F	
Thermal Conductivity	240 W/m-K	1670 BTU-in/hr-ft ² -°F	
Melting Point	1040 - 1080 °C	1900 - 1980 °F	
Solidus	1040 °C	1900 °F	
Liquidus	1080 °C	1980 °F	

Component Elements Properties	Metric	English	Comments
Beryllium, Be	0.20 - 0.60 %	0.20 - 0.60 %	
Copper, Cu	98 %	98 %	as balance
Nickel, Ni	1.4 - 2.2 %	1.4 - 2.2 %	

Electrical Properties	Metric	English	Comments
	0.00000290 -	0.00000290 -	

Electrical Resistivity Electrical Properties	0.00000380 ohm-cm Metric	0.00000380 ohm-cm English	45-60% IACS Conductivity Comments
---	-----------------------------	------------------------------	--------------------------------------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China