

Materion Beryllium Copper Alloy M25 Wire; 1/2H (TD02) Temper; 1.3-12.7 mm Diameter (UNS C17300)

Category : Metal , Nonferrous Metal , Beryllium Alloy , Copper Alloy

Material Notes:

Treatment required for max strength: as supplied
Tabulated properties apply to products after age hardening. Information supplied by Brush Wellman. Brush Engineered Materials Inc. changed its name to Materion Corporation in March 2011.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Materion-Beryllium-Copper-Alloy-M25-Wire-12H-TD02-Temper-13-127-mm-Diameter-UNS-C17300.php

Physical Properties	Metric	English	Comments
Density	8.36 g/cc	0.302 lb/in ³	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	750 - 940 MPa	109000 - 136000 psi	
Tensile Strength, Yield	620 - 870 MPa	89900 - 126000 psi	
Elongation at Break	2.0 - 15 %	2.0 - 15 %	
Modulus of Elasticity	131 GPa	19000 ksi	
Machinability	60 %	60 %	

Thermal Properties	Metric	English	Comments
CTE, linear	17.0 $\mu\text{m/m-}\text{^\circ}\text{C}$	9.44 $\mu\text{in/in-}\text{^\circ}\text{F}$	
	@Temperature 20.0 - 200 $\text{^\circ}\text{C}$	@Temperature 68.0 - 392 $\text{^\circ}\text{F}$	
Thermal Conductivity	105 W/m-K	729 BTU-in/hr-ft ² - $\text{^\circ}\text{F}$	
Melting Point	870 - 980 $\text{^\circ}\text{C}$	1600 - 1800 $\text{^\circ}\text{F}$	
Solidus	870 $\text{^\circ}\text{C}$	1600 $\text{^\circ}\text{F}$	
Liquidus	980 $\text{^\circ}\text{C}$	1800 $\text{^\circ}\text{F}$	

Component Elements Properties	Metric	English	Comments
Beryllium, Be	1.8 - 2.0 %	1.8 - 2.0 %	
Co + Ni	≥ 0.20 %	≥ 0.20 %	
Co + Ni + Fe	≤ 0.60 %	≤ 0.60 %	
Copper, Cu			as balance

Component Elements Properties	97.5 % Metric	97.5 % English	Comments
Lead, Pb	0.20 - 0.60 %	0.20 - 0.60 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.00000910 - 0.0000115 ohm-cm	0.00000910 - 0.0000115 ohm-cm	15-19% IACS Conductivity

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China