

Materion Beryllium Nickel Strip - Alloy 360 MH2, Mill Hardened

Category : Metal , Nonferrous Metal , Beryllium Alloy , Nickel Alloy

Material Notes:

Information supplied by Brush Wellman Engineered Materials. Treatment required for max strength: Mill Hardened Stress Relaxation-% Stress Remaining after 1000 hrs @ 100°C: 99% Stress Relaxation after 1000 hrs @ 200°C: 98% Formability Ratio, 90° Bend, Radius/Thickness (Good Way): 0 Formability Ratio (bad Way): 0 Brush Wellman's Alloy 360 beryllium nickel strip combines unique mechanical and physical properties required in today's high reliability electrical/electronic systems, heavy duty controls, electromechanical devices and in other high performance applications. Properties of beryllium nickel Alloy 360 strip that a designer can use include ultimate tensile strength approaching 300,000 psi, yield strength up to 245,000 psi, excellent formability, stress relaxation less than 5% at 400°F, and fatigue strength (in reverse bending) of 85,000 - 90,000 psi at 10 million cycles. Typically, this alloy is used for mechanical and electrical/electronic components that are subjected to elevated temperatures (up to 700°F for short times), and require good spring characteristics at these temperatures. Some applications for this alloy are thermostats, bellows, diaphragms, burn-in connectors, and sockets. Brush Engineered Materials Inc. changed its name to Materion Corporation in March 2011.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Materion-Beryllium-Nickel-Strip-Alloy-360-MH2-Mill-Hardened.php

| Physical Properties | Metric | English | Comments |
|---------------------|-----------|--------------------------|----------|
| Density | 8.28 g/cc | 0.299 lb/in ³ | |

| Mechanical Properties | Metric | English | Comments |
|----------------------------|-----------------|---------------------|----------|
| Tensile Strength, Ultimate | 1070 - 1241 MPa | 155000 - 180000 psi | |
| Tensile Strength, Yield | 862 - 960 MPa | 125000 - 139000 psi | |
| Elongation at Break | >= 14 % | >= 14 % | |
| Modulus of Elasticity | 195 - 210 GPa | 28300 - 30500 ksi | |

| Thermal Properties | Metric | English | Comments |
|----------------------|-----------------------------|-----------------------------|----------|
| CTE, linear | 14.0 Åµm/m-Å°C | 7.78 Åµin/in-Å°F | |
| | @Temperature 20.0 - 200 Å°C | @Temperature 68.0 - 392 Å°F | |
| Thermal Conductivity | 48.0 W/m-K | 333 BTU-in/hr-ftÅ²-Å°F | |
| Melting Point | 1195 - 1325 Å°C | 2183 - 2417 Å°F | |
| Solidus | 1195 Å°C | 2183 Å°F | |
| Liquidus | 1325 Å°C | 2417 Å°F | |

| Component Elements Properties | Metric | English | Comments |
|-------------------------------|--------|---------|----------|
|-------------------------------|--------|---------|----------|

| Component Elements Properties | Metric | English | Comments |
|-------------------------------|---------------|---------------|------------|
| Copper, Cu | <= 0.25 % | <= 0.25 % | |
| Nickel, Ni | 97.3 % | 97.3 % | as balance |
| Titanium, Ti | 0.40 - 0.60 % | 0.40 - 0.60 % | |

| Electrical Properties | Metric | English | Comments |
|------------------------|---------------------|---------------------|--------------------------------|
| Electrical Resistivity | <= 0.0000344 ohm-cm | <= 0.0000344 ohm-cm | 5% IACS conductivity (minimum) |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China