

Materion BrushBronze® 95510 (AMS 4880) Continuous Cast 0.250" - 4.0"

Category: Metal, Nonferrous Metal, Copper Alloy, Bronze, Copper Casting Alloy

Material Notes:

Information supplied by Brush Wellman Engineered Materials.BrushBronzeâ,,¢ 95510 is an Aluminum-Nickel-Bronze alloy that combines high strength, ductility, and good abrasion resistance under severe loading conditions. This material, specified as AMS 4880, is frequently used for very demanding aerospace applications, including, but not limited to: bushings, spherical and rod end bearings, rub pads, and wear strips. This material is also commonly used for applications in the oil and gas and other durable goods markets.BrushBronzeâ,,¢ 95510 (AMS 4880) offers several significant advantages over other materials available in the marketplace due to the EquaCastâ,,¢ process:Higher and more consistent mechanical propertiesImproved service lifeSuperior qualityEase of useCost effectivenessBrush Engineered Materials Inc. changed its name to Materion Corporation in March 2011.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Materion-BrushBronze-95510-AMS-4880-Continuous-Cast-0250-40.php

| Mechanical Properties | Metric | English | Comments |
|----------------------------|---------|------------|----------|
| Tensile Strength, Ultimate | 724 MPa | 105000 psi | |
| Tensile Strength, Yield | 431 MPa | 62500 psi | |
| Elongation at Break | 9.0 % | 9.0 % | |

| Component Elements Properties | Metric | English | Comments |
|-------------------------------|--------------|--------------|----------|
| Aluminum, Al | 9.7 - 10.9 % | 9.7 - 10.9 % | |
| Copper, Cu | >= 78 % | >= 78 % | |
| Iron, Fe | 2.0 - 3.5 % | 2.0 - 3.5 % | |
| Manganese, Mn | <= 1.5 % | <= 1.5 % | |
| Nickel, Ni | 4.5 - 5.5 % | 4.5 - 5.5 % | |
| Tin, Sn | <= 0.20 % | <= 0.20 % | |
| Zinc, Zn | <= 0.30 % | <= 0.30 % | |

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China