

Materion E20 Beryllium/BeO Composite, 20 Volume% BeO

Category : Metal , Metal Matrix Composite , Nonferrous Metal , Beryllium Alloy

Material Notes:

Metal matrix composite made up principally of beryllium and crystal BeO platelets. Produced by blending the beryllium and beryllium oxide powders into a homogeneous mixture to create isotropic properties. This mix is hot isostatically pressed (HIP'd) into fully dense blocks for further processing into finished blanks and subsequent machining into components. These materials are used in electronic packaging heat sinks for MCM-L, SEM-E, BGA's, and RF/Microwave applications. The CTE can be controlled by varying the BeO content to match with die materials like GaAs or silicon in RF/microwave applications or match AuSn or AuGe over brazing/soldering temperatures, Kovar, Alloy 46 or 48, and other packaging materials. Can be machined by conventional processes. Corrosion resistance similar to aluminum. For protection in severe environments such as salt fog, the composite may be coated in a number of ways such as electroless or electrolytic nickel plating, chrome plating, and gold or silver plating for brazing or soldering operations. Please note that there are health hazards associated with beryllium, especially when present as airborne particles generated during processing. As with any material, be aware of hazards and take steps to reduce exposure to a safe level. Information provided by Brush Wellman. Brush Engineered Materials Inc. changed its name to Materion Corporation in March 2011.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Materion-E20-BerylliumBeO-Composite-20-Volume-BeO.php

Physical Properties	Metric	English	Comments
Density	2.06 g/cc	0.0744 lb/in ³	Average. Minimum bulk density is 2.045 g/cc.

Mechanical Properties	Metric	English	Comments
Modulus of Elasticity	>= 301 GPa	>= 43700 ksi	Minimum
	303 GPa	43900 ksi	Typical
Fracture Toughness	13.7 MPa-m ^{1/2}	12.5 ksi-in ^{1/2}	Average K _{IC} .

Thermal Properties	Metric	English	Comments
CTE, linear	9.50 - 11.0 $\mu\text{m/m-}^\circ\text{C}$	5.28 - 6.11 $\mu\text{in/in-}^\circ\text{F}$	
	@Temperature 25.0 - 100 $^\circ\text{C}$	@Temperature 77.0 - 212 $^\circ\text{F}$	
	11.5 $\mu\text{m/m-}^\circ\text{C}$	6.39 $\mu\text{in/in-}^\circ\text{F}$	average
	@Temperature 25.0 - 250 $^\circ\text{C}$	@Temperature 77.0 - 482 $^\circ\text{F}$	
Specific Heat Capacity	1.584 J/g- $^\circ\text{C}$	0.3786 BTU/lb- $^\circ\text{F}$	
Thermal Conductivity	>= 200 W/m-K	>= 1390 BTU-in/hr-ft ² - $^\circ\text{F}$	Minimum
		1460 BTU-in/hr-ft ² -	

Thermal Properties	210 W/m-K Metric	A°F English	Typical Comments
Component Elements Properties	Metric	English	Comments
BeO	25.8 - 32.25 %	25.8 - 32.25 %	
Beryllium, Be	79.37 - 83.5 %	79.37 - 83.5 %	As remainder; includes Be from BeO
Oxygen, O	16.5 - 20.63 %	16.5 - 20.63 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China