

## Mearthane Durethane F DF-630A Closed Cell Foam Polyurethane

Category : Polymer , Thermoset , Polyurethane, TS , Thermoset Polyurethane Foam, Unreinforced , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

MDI backbone: ester. Shore 00 Hardness: 75 Summary: Durethane F is chemically blown urethane closed cell foam. Mearthane can custom formulate Durethane F, varying the physical properties (coefficient of friction, abrasion resistance, hardness and density) to suit various application. The rebound can be formulated for resiliency or energy absorption. Applications: Applications for Durethane F include self-cleaning paper feed rollers, retard pads, conveyor belts, bumpers shock absorbers and timing belts. Conductivity: All Durethane elastomers can be formulated to be electrically conductive, for applications involving electrostatic dissipation (ESD). Mearthane's proprietary conductivity process does not comprise the material performance specification of the urethane. Information provided by Mearthane Products Corporation.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Mearthane-Durethane-F-DF-630A-Closed-Cell-Foam-Polyurethane.php](http://www.lookpolymers.com/polymer_Mearthane-Durethane-F-DF-630A-Closed-Cell-Foam-Polyurethane.php)

Physical Properties	Metric	English	Comments
Density	0.480 g/cc	0.0173 lb/in <sup>3</sup>	ASTM D3574A

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	30	30	ASTM D2240
Tensile Strength, Ultimate	32.4 MPa	4700 psi	ASTM D3574E
Elongation at Break	600 %	600 %	ASTM 3457E
100% Modulus	0.000965 GPa	0.140 ksi	
Compressive Yield Strength	0.340 MPa	49.3 psi	at 10% deflection; ASTM D3574C
	0.520 MPa	75.4 psi	at 20% deflection; ASTM D3574C
	0.860 MPa	125 psi	at 30% deflection; ASTM D3574C
Resilience	39	39	Bashore Rebound; ASTM 2632D
Tear Strength Test	105	105	lb; Die C; ASTM 3457F

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China