

Mearthane Durethane,ç M DM-710A Foam Polyurethane

Category : Polymer , Thermoset , Polyurethane, TS , Thermoset Polyurethane Foam, Unreinforced , Rubber or Thermoset Elastomer (TSE)

Material Notes:

MDI backbone: ether. Shore 00 Hardness: 55 Summary: Durethane M is a flexible, microcellular, open cell and closed cell urethane foam.

Because it is mechanically mixed, the cell size is uniform. Durethane M is very economical, and has excellent resistance to compression set.

It can be formulated to form an integral skin. Applications: The compression set resistance of Durethane M makes it an effective material for

applications with repeated compression cycles, such as actuator pads on postal meters and idler belts. Conductivity: All Durethane

elastomers can be formulated to be electrically conductive, for applications involving electrostatic dissipation (ESD). Mearthane's

proprietary conductivity process does not comprise the material performance specification of the urethane. Information provided by

Mearthane Products Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Mearthane-Durethane-M-DM-710A-Foam-Polyurethane.php

Physical Properties	Metric	English	Comments
Density	0.320 g/cc	0.0116 lb/in ³	ASTM D3574A

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	10	10	ASTM D2240
Tensile Strength, Ultimate	6.90 MPa	1000 psi	ASTM D3574E
Elongation at Break	340 %	340 %	ASTM 3457E
100% Modulus	0.000276 GPa	0.0400 ksi	ASTM D3574E
200% Modulus	0.000620 GPa	0.0899 ksi	ASTM D3574E
Compressive Yield Strength	0.0300 MPa	4.35 psi	at 10% deflection; ASTM D3574C
	0.0380 MPa	5.51 psi	at 20% deflection; ASTM D3574C
	0.0500 MPa	7.25 psi	at 30% deflection; ASTM D3574C
Resilience	43	43	Bashore Rebound; ASTM 2632D
Tear Strength Test	30	30	lb; Die C; ASTM 3457F

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China