

## **Meehanite K-405 Austempered Ductile Iron**

Category: Metal, Ferrous Metal, Cast Iron, Alloy Cast Iron, Ductile Iron

## **Material Notes:**

Type K-405 is for applications involving wear and requiring high tensile and endurance limit. Excellent founding properties enable more accurate castings with savings in machine stock required. Damping capacity and notch sensitivity are superior to steel castings and forgings. Self-lubricating properties make Type K-405 ideal for wear conditions involving minimal lubrication. General Meehanite information - Meehanite metal is first melted to a definite degree of undercooling or constitution which is related to the section of the casting to be poured and the range of physical properties such as tensile strength and hardness required. Nucleation with patented mixtures of graphitizing agents results in the removal of undercooling, in the controlled precipitation of graphite and in a fine grained eutectic cell structure which determines the density and physical integrity of the casting. Ordinary cast irons made to chemical specifications which do not include the benefit of controlled undercooling are influenced by mass effect to a maximum degree and for this and other reasons cannot be considered an equivalent to Meehanite metal. Information provided by Meehanite Marketing Association.

Order this product through the following link:

http://www.lookpolymers.com/polymer\_Meehanite-K-405-Austempered-Ductile-Iron.php

Mechanical Properties	Metric	English	Comments
Hardness, Brinell	380 - 430	380 - 430	
Tensile Strength, Ultimate	1210 MPa	175000 psi	
Tensile Strength, Yield	965 MPa	140000 psi	
Elongation at Break	2.0 - 5.0 %	2.0 - 5.0 %	
Fatigue Strength	352 MPa	51000 psi	Endurance Limit (Notched)
	510 MPa	74000 psi	Endurance Limit (Unnotched)

## Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China