

Mi-Tech Metals HD17.5 Tungsten-Based Metal

Category : Metal , Nonferrous Metal , Refractory Metal , Tungsten Alloy

Material Notes:

Mil Spec T-21014D Class 2; AMS T-21014 Class 2; ASTM B-777-99 Class 2; ASTM B-777-07 Class 2. Slightly Magnetic. Manufactured by powder metallurgy methods. The tungsten base offers high thermal conductivity and a low CTE which combine to resist thermal fatigue. The high melting point reduces soldering or erosion problems. To increase the machinability of this brittle metal, alloying elements are added and practical use of tungsten is possible for die casting tools. Used in resistance brazing and high temp applications. Used as counter weights and counter balances, radiation shielding components, tool shanks for boring bars and other tools for chatter-free machining. Data provided by Mi-Tech Metals.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Mi-Tech-Metals-HD175-Tungsten-Based-Metal.php

Physical Properties	Metric	English	Comments
Density	17.5 g/cc	0.632 lb/in ³	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell C	33	33	
Tensile Strength, Ultimate	786 MPa	114000 psi	
Tensile Strength, Yield	580 MPa @Strain 0.200 %	84100 psi @Strain 0.200 %	
Elongation at Break	7.0 %	7.0 %	in 50 mm
Modulus of Elasticity	324 GPa	47000 ksi	

Thermal Properties	Metric	English	Comments
CTE, linear	4.62 $\mu\text{m/m-}^\circ\text{C}$ @Temperature 20.0 - 400 $^\circ\text{C}$	2.57 $\mu\text{in/in-}^\circ\text{F}$ @Temperature 68.0 - 752 $^\circ\text{F}$	
Thermal Conductivity	84.0 W/m-K	583 BTU-in/hr-ft ² - $^\circ\text{F}$	

Component Elements Properties	Metric	English	Comments
Iron, Fe	2.5 %	2.5 %	
Nickel, Ni	5.25 %	5.25 %	
Tungsten, W	92.5 %	92.5 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.0000130 ohm-cm	0.0000130 ohm-cm	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China