

Michelman® Michem® Emulsion 66035 Anionic paraffin/polyethylene wax emulsion

Category : Fluid , Other Engineering Material , Additive/Filler for Polymer , Polymer , Thermoplastic , Polyethylene (PE)

Material Notes:

Description: Anionic paraffin/polyethylene wax emulsion
Usage: Michem® Emulsion 66035 is an excellent waterbeading agent for exterior coatings providing early water beading and anti-blocking properties as well. Michem® Emulsion 66035 also is successfully used for hot tire scuff resistance in asphalt. We serve many markets through Michem® Emulsion, including: paint & coatings; fiberglass; inks and overprint varnishes; floor care; wood finishes; automotive care products; building products; carpets; die lubricants; fruit and vegetable coatings; textiles and urethane foam
Food Contact Information when manufactured in the USA: FDA:175.105: Components of adhesives. 175.300: Resinous and polymeric components of coatings. 175.320: Resinous and polymeric components of coatings for polyolefin films. 176.170: Components of paper and paperboard in contact with aqueous and fatty foods. 176.180: Components of paper and paperboard in contact with dry foods. When manufactured in USA product meets food contact regulations for: Europe: Euro. Res. AP(2004)1
Food Contact Information when manufactured in Belgium: FDA:175.105: Components of adhesives. 175.300: Resinous and polymeric components of coatings. (Restricted) 175.320: Resinous and polymeric components of coatings for polyolefin films. (Restricted) 176.170: Components of paper and paperboard in contact with aqueous and fatty foods. (Restricted) 176.180: Components of paper and paperboard in contact with dry foods. When manufactured in Belgium product meets food contact regulations for: Europe: Euro. Res. AP(2004)1 (Restricted) and Commission Regulation (EU) n° 10/2011 (Restricted) Germany: BfR Recommendation XIV (Restricted) and BfR Recommendation XXXVI (Restricted)
Food Contact Information when manufactured in Singapore: FDA:175.105: Components of adhesives. 175.300: Resinous and polymeric components of coatings. 175.320: Resinous and polymeric components of coatings for polyolefin films. 176.170: Components of paper and paperboard in contact with aqueous and fatty foods. (Restricted) 176.180: Components of paper and paperboard in contact with dry foods. Information provided by Michelman®

Order this product through the following link:

http://www.lookpolymers.com/polymer_Michelman-Michem-Emulsion-66035-Anionic-paraffinpolyethylene-wax-emulsion.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.950 - 0.970 g/cc	0.950 - 0.970 g/cc	
Volatiles	64.5 - 65.5 %	64.5 - 65.5 %	
pH	>= 7.0	>= 7.0	Recommended pH of system
	9.3 - 10.3	9.3 - 10.3	
Brookfield Viscosity	<= 100 cP	<= 100 cP	Spindle # 1, rpm 60

Descriptive Properties	Value	Comments
Appearance	Cream colored liquid	
Emulsifier Charge	Anionic	
Solids Type	Paraffin/Polyethylene Wax blend	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China