

**Michelman® Michem® Emulsion 93235 Nonionic polyethylene emulsion**

Category : Fluid , Other Engineering Material , Additive/Filler for Polymer , Polymer , Thermoplastic , Polyethylene (PE)

**Material Notes:**

Description: Nonionic polyethylene emulsion Usage: Michem® Emulsion 93235 is a phenol free additive best used in water based coatings where improved slip, rub resistance, hardness and/or block resistance is needed. Michem® Emulsion 93235 has proven very effective for mar resistance in floor polish formulations as well as mar resistance and shine in car polish formulations. We serve many markets through Michem® Emulsion, including: paint & coatings; fiberglass; inks and overprint varnishes; floor care; wood finishes; automotive care products; building products; carpets; die lubricants; fruit and vegetable coatings; textiles and urethane foam When manufactured in Belgium product meets food contact regulations for: Europe: Euro. Res. AP(2004)1 Germany: BfR Recommendation XXXVI (Restricted) Food Contact Information when manufactured in Belgium: FDA:175.105: Components of adhesives. 176.170: Components of paper and paperboard in contact with aqueous and fatty foods. 176.180: Components of paper and paperboard in contact with dry foods. Information provided by Michelman®

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Michelman-Michem-Emulsion-93235-Nonionic-polyethylene-emulsion.php](http://www.lookpolymers.com/polymer_Michelman-Michem-Emulsion-93235-Nonionic-polyethylene-emulsion.php)

Physical Properties	Metric	English	Comments
Specific Gravity	0.990 - 1.01 g/cc	0.990 - 1.01 g/cc	
Volatiles	64.5 - 65.5 %	64.5 - 65.5 %	
pH	>= 7.0	>= 7.0	Recommended pH of system
	8.5 - 10.5	8.5 - 10.5	
Brookfield Viscosity	<= 50 cP	<= 50 cP	Spindle # 1, rpm 60

Descriptive Properties	Value	Comments
Appearance	Translucent liquid	
Emulsifier Charge	Nonionic	
Solids Type	High Density Polyethylene	

**Contact Songhan Plastic Technology Co.,Ltd.**Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China