

Michelman® Michem® Glide 37 Nonionic PTFE dispersion

Category : Fluid , Other Engineering Material , Additive/Filler for Polymer , Polymer , Thermoplastic , Fluoropolymer , PTFE

Material Notes:

Description: Nonionic PTFE dispersion Usage: Michem® Glide 37 as an additive provides mar, abrasion and high temperature resistance for a variety of applications within the paint and coating industries. Michem® Glide 37 also improves slip in coatings. Typical uses include: Inks and OPVs; Exterior wood and wood composites and Interior furniture and flooring Food Contact Information when manufactured in the USA: FDA:175.105: Components of adhesives 175.300: Resinous and polymeric components of coatings. 176.170: Components of paper and paperboard in contact with aqueous and fatty foods. (Restricted) 176.180: Components of paper and paperboard in contact with dry foods. (Restricted) Food Contact Information when manufactured in Belgium: FDA:175.105: Components of adhesives. 176.170: Components of paper and paperboard in contact with aqueous and fatty foods. (Restricted) 176.180: Components of paper and paperboard in contact with dry foods. (Restricted) Information provided by Michelman®

Order this product through the following link:

http://www.lookpolymers.com/polymer_Michelman-Michem-Glide-37-Nonionic-PTFE-dispersion.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.45 - 1.47 g/cc	1.45 - 1.47 g/cc	
Volatiles	49.5 - 50.5 %	49.5 - 50.5 %	
pH	3.0 - 7.0	3.0 - 7.0	
	2.0 - 12	2.0 - 12	Recommended pH of system
Brookfield Viscosity	<= 5000 cP	<= 5000 cP	Spindle # 4, rpm 60

Descriptive Properties	Value	Comments
Appearance	White, viscous liquid	
Emulsifier Charge	Nonionic	
Solids Type	PTFE	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China