

Michelman® Michem® In-Line Primer Q4305A Primer

Category : Fluid , Other Engineering Material , Additive/Filler for Polymer

Material Notes:

Description: Michem® In-Line Primer Q4305A is a primer for print receptivity for use with HP Indigo press W3250. Usage: Michem® In-Line Primer Q4305A is designed as a primer for HP Indigo substrates to render them compatible to ink. It can be used on uncoated paper substrates on the in-line priming unit on the W3250 press. Application Data: Michem® In-Line Primer Q4304A can be applied using the in-line primer unit on the W3250 press. The recommended dry coat weight is 30 to 60 mg/m². Use our Sapphire Indicator Solution to check quality of the coating. The anilox should be kept turning at all times to avoid premature drying of the solution. Cleaning with warm water, IPA or slightly acidic water is recommended. Michem® In-Line Primer Q4305A can be applied using the in-line primer unit on the W3250 press. The recommended dry coat weight is 30 to 60 mg/m². Use our Sapphire Indicator Solution to check quality of the coating. The anilox should be kept turning at all times to avoid premature drying of the solution. Cleaning with warm water, IPA or slightly acidic water is recommended. Information provided by Michelman®

Order this product through the following link:

http://www.lookpolymers.com/polymer_Michelman-Michem-In-Line-Primer-Q4305A-Primer.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.980 - 1.02 g/cc	0.980 - 1.02 g/cc	
pH	<= 11	<= 11	
Brookfield Viscosity	40 - 50 cP	40 - 50 cP	Spindle # 3, rpm 60

Descriptive Properties	Value	Comments
Appearance	Translucent liquid	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China