

## Michelman® Michem® Lube 193 Slip and anti-block additive

Category : Fluid , Other Engineering Material , Additive/Filler for Polymer

**Material Notes:**

Description: Slip and anti-block additive for latex systems Compatible with ingredients used in many industries, including: Automotive care products; Building materials; Can and coil coatings; Concrete; Cordage and twine; Deck stains and sealants; Die lubricants; Fiber sizings; Floor polishes; Furniture coatings; Glass; Gloves, balloons, footwear and mechanical seals; Inks; Packaging films; Pressure-sensitive adhesives; Textiles; Urethane foam and Varnishes When manufactured in the USA product meets food contact regulations for: Europe: Euro. Res. AP(2004)1 (Restricted) and Commission Regulation (EU) n° 10/2011 Germany: BfR Recommendation XIV (Restricted) Food Contact Information when manufactured in the USA: FDA:175.105: Components of adhesives. 175.320: Resinous and polymeric components of coatings for polyolefin films. 176.170: Components of paper and paperboard in contact with aqueous and fatty foods. 176.180: Components of paper and paperboard in contact with dry foods. When manufactured in Singapore product meets food contact regulations for: Europe: Euro. Res. AP(2004)1 (Restricted) and Commission Regulation (EU) n° 10/2011 (Restricted) Germany: BfR Recommendation XIV (Restricted) and BfR Recommendation XXXVI (Restricted) Information provided by Michelman®

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Michelman-Michem-Lube-193-Slip-and-anti-block-additive.php](http://www.lookpolymers.com/polymer_Michelman-Michem-Lube-193-Slip-and-anti-block-additive.php)

Physical Properties	Metric	English	Comments
Specific Gravity	0.990 - 1.01 g/cc	0.990 - 1.01 g/cc	
Volatiles	74.5 - 75.5 %	74.5 - 75.5 %	
pH	>= 7.0	>= 7.0	Recommended pH of system
	8.7 - 9.3	8.7 - 9.3	
Brookfield Viscosity	<= 40 cP	<= 40 cP	Spindle # 1, rpm 60

Descriptive Properties	Value	Comments
Appearance	Brown emulsion with light cream on top	
Emulsifier Charge	Anionic	
Solids Type	Carnauba	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China