

Michelman® Michem® Lube 743 Nonionic paraffin wax emulsion

Category : Fluid , Other Engineering Material , Additive/Filler for Polymer

Material Notes:

Description: Nonionic paraffin wax emulsion
Usage: Michem® Lube 743 exhibits a high degree of water resistance and excellent compatibility. This product is used in many water based coating applications to increase water resistance and/or surface slip. Compatible with ingredients used in many industries, including: Automotive care products; Building materials; Can and coil coatings; Concrete; Cordage and twine; Deck stains and sealants; Die lubricants; Fiber sizings; Floor polishes; Furniture coatings; Glass; Gloves, balloons, footwear and mechanical seals; Inks; Packaging films; Pressure-sensitive adhesives; Textiles; Urethane foam and Varnishes
When manufactured in the USA product meets food contact regulations for: Europe: Euro. Res. AP(2004)1 (Restricted) and Commission Regulation (EU) n° 10/2011(Restricted) Germany: BfR Recommendation XIV (Restricted) and BfR Recommendation XXXVI (Restricted)
Food Contact Information when manufactured in the USA: FDA:175.105: Components of adhesives. 175.320: Resinous and polymeric components of coatings for polyolefin films. (Restricted) 176.170: Components of paper and paperboard in contact with aqueous and fatty foods. 176.180: Components of paper and paperboard in contact with dry foods. **Food Contact Information when manufactured with Singapore:** FDA:175.105: Components of adhesives. 175.320: Resinous and polymeric components of coatings for polyolefin films.
 Information provided by Michelman®

Order this product through the following link:

http://www.lookpolymers.com/polymer_Michelman-Michem-Lube-743-Nonionic-paraffin-wax-emulsion.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.980 - 1.00 g/cc	0.980 - 1.00 g/cc	
Volatiles	67.5 - 68.5 %	67.5 - 68.5 %	
pH	6.0 - 7.5	6.0 - 7.5	
Brookfield Viscosity	<= 150 cP	<= 150 cP	Spindle # 2, rpm 60

Descriptive Properties	Value	Comments
Appearance	White, low viscosity liquid	
Emulsifier Charge	Nonionic	
Solids Type	Paraffin	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China