

Michelman[®] Sapphire 5.0 Ink Primer

Category : Fluid , Other Engineering Material , Additive/Filler for Polymer

Material Notes:

Primer for use with HP Indigo press.Q4310A (Sapphire 5.0) is designed as a primer for HP Indigo substrates to render them compatible to ink. It can be used on paper substrates.Q4310A (Sapphire 5.0) can be applied via flexo or direct gravure systems. The recommended dry coat weight is 30 to 60 mg/m². Use our Sapphire Indicator Solution to check quality of the coating. The anilox should be kept turning at all times to avoid premature drying of the solution. Cleaning with warm water, IPA or slightly acidic water is recommended.Information provided by Michelman[®]

Order this product through the following link:

http://www.lookpolymers.com/polymer_Michelman-Sapphire-50-Ink-Primer.php

| Physical Properties | Metric | English | Comments |
|----------------------|-------------------|-------------------|---------------------|
| Specific Gravity | 0.980 - 1.02 g/cc | 0.980 - 1.02 g/cc | |
| Volatiles | 94.75 - 95.25 % | 94.75 - 95.25 % | |
| pH | <= 11 | <= 11 | |
| Brookfield Viscosity | 30 - 35 cP | 30 - 35 cP | Spindle # 3, rpm 60 |

| Descriptive Properties | Value | Comments |
|------------------------|--------------------|----------|
| Appearance | Translucent liquid | |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China