

Microcell Composite Company CELLAMP® 5000 Pellets

Category : Polymer , Thermoplastic

Material Notes:

CELLAMP® Pellets can be used for producing foaming boards with damping properties, which yield the best efficiency between -10°C and room temperature. Information provided by Microcell Composite Company

Order this product through the following link:

http://www.lookpolymers.com/polymer_Microcell-Composite-Company-CELLAMP-5000-Pellets.php

Physical Properties	Metric	English	Comments
Density	0.940 g/cc	0.0340 lb/in ³	
Melt Flow	21.7 g/10 min @Load 5.00 kg, Temperature 190 °C	21.7 g/10 min @Load 11.0 lb, Temperature 374 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	63	63	
Tensile Strength, Yield	7.73 MPa	1120 psi	
Elongation at Yield	629 %	629 %	
Tear Strength	26.03 kN/m	148.7 pli	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China