

## Microcell Composite Company CELLOMER<sup>®</sup> 2100 SBS Rubber Pellets

Category : Polymer , Thermoplastic , Styrene-Butadiene , Styrene/Butadiene/Styrene (SBS)

### Material Notes:

CELLOMER<sup>®</sup> PELLETS can be used in hot-pressing or with injection foaming boards. Featuring anti-slippage and elasticity. Information provided by Microcell Composite Company

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Microcell-Composite-Company-CELLOMER-2100-SBS-Rubber-Pellets.php](http://www.lookpolymers.com/polymer_Microcell-Composite-Company-CELLOMER-2100-SBS-Rubber-Pellets.php)

Physical Properties	Metric	English	Comments
Density	0.930 g/cc	0.0336 lb/in <sup>3</sup>	
Melt Flow	3.617 g/10 min @Load 5.00 kg, Temperature 190 °C	3.617 g/10 min @Load 11.0 lb, Temperature 374 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	51	51	
Tensile Strength, Yield	6.515 MPa	944.9 psi	
Elongation at Yield	625 %	625 %	
Tear Strength	36.15 kN/m	206.5 pli	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China